

**PLEXIGLAS®**  
Solid Sheet and Tube

**PLEXIGLAS® Satinice**

**Product**

With its warm and soft appearance, the velvety surface of PLEXIGLAS® Satinice simply cries out to be touched. Due to its translucency, the material looks especially attractive in combination with light.

This surface makes the material insensitive to traces of wear and finger marks. PLEXIGLAS® Satinice is available with a satin surface on one side (SC) or on both sides (DC), and in a grade with diffuser beads that are evenly distributed throughout the material, not just at the surface (DF).

**Properties**

In addition to the well-known and time-tested properties of PLEXIGLAS®, such as

- excellent light transmission and brilliance
- very high weather resistance
- ease of fabrication
- low weight – about half the weight of glass
- 11 times the impact strength of glass
- 100% recyclability

PLEXIGLAS® Satinice offers the following special features:


- white grades with varying degrees of light diffusion
- balanced ratio of light diffusion and transmittance
- insensitivity to traces of wear

**Surfaces and other properties of the various products:**




**Cast sheet**

- + light-diffusing
- + extremely easy to machine and fabricate
- + wide range of thicknesses and colors available from stock
- + insensitive surface



**Extruded sheet**

- + light-diffusing
- + low thickness tolerance
- + tough surface due to diffuser beads
- + texture is retained after thermoforming



### Extruded sheet with optimum light diffusion

- + light-diffusing beads evenly distributed throughout the material
- + texture is retained after thermoforming
- + good balance between light diffusion and light transmission.



### Tubes: frosted, optimum light diffusion, extruded

- + light-diffusing beads evenly distributed throughout the material

### Applications

These properties make PLEXIGLAS® Satinice especially suitable for

- counters, shelves, tables, chairs, displays in furniture, exhibition booths and store fixtures
- wall paneling in architectural applications
- white-translucent grades as covers for lamps and skylights (especially ODO10 DF)
- tubes as luminaires or lighting elements

### Fabrication

PLEXIGLAS® Satinice can be fabricated just like standard PLEXIGLAS®. The following Guidelines for Workshop Practice are available for PLEXIGLAS®:

- Machining PLEXIGLAS® (No. 311-1)
- Forming PLEXIGLAS® (No. 311-2)
- Joining PLEXIGLAS® (No. 311-3)
- Fabricating Tips for PLEXIGLAS® Solid Sheets (No. 311-5)

### Physical forms

PLEXIGLAS® Satinice is available in the following colors, sizes and thicknesses:

### PLEXIGLAS® Satinice – colors

	clear	white translucent	colors
Cast sheet	OF00 DC OF00 SC	WH02 DC WH02 SC WH10 DC	many colors
Extruded sheet	OM033 DC OM033 SC	WM513 DC WM513 SC	on request
optimum light diffusion, extruded	OD010 DF	on request	on request
optimum light diffusion, extruded tubes	OD010 DF	WD300 DF	on request

DC = satin surface on both sides;

SC = satin surface on one side;

DF = satin surface on both sides / beads evenly distributed

**PLEXIGLAS® Satinice – technical values**

	Transmission (T <sub>D65</sub> )*	Half-value angle*
OF00 SC/DC	92 %	
WH02 SC/DC	44 %	
WH10 DC	70 %	
OM033 SC/DC	92 %	
WM513 SC/DC	70 %	
OD010 DF	83 %	
WD300 DF	21 %	56°

\* The light transmission and the half-value angle are given as a typical value for 3 mm thickness. It is measured according to test standard DIN 5036.

**PLEXIGLAS® Satinice – sizes**

	Size	Thicknesses
Cast sheet	3050x2030 mm	3–20 mm
Extruded sheet	3050x2050 mm	3–10 mm
optimum light diffusion, extruded	3050x2050 mm	3–6 mm
extruded tubes	Ø 50–Ø 200 mm	3 mm (wall)

You can find the complete range of products in the PLEXIGLAS® Sales Range.

**Röhm GmbH**  
Acrylic Products

Riedbahnstraße 70  
64331 Weiterstadt  
Germany

**www.plexiglas.de**  
**www.roehm.com**

® = registered trademark  
PLEXIGLAS is a registered trademark of Röhm GmbH, Darmstadt, Germany.  
Certified to DIN EN ISO 9001 (Quality) and DIN EN ISO 14001 (Environment)

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments.

The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.